

EUROPEAN METALS HOLDINGS LIMITED

CINOVEC MAIDEN ORE RESERVE, BOARD CHANGES, INTERIM FUNDING

European Metals Holdings Limited ("European Metals" or "the Company") (ASX and AIM: EMH) is pleased to declare the maiden Ore Reserve at the Company's Cinovec Lithium / Tin Project in the Czech Republic. In addition, the Company has appointed Mr Richard Pavlik to the Board of Directors, and secured short-term funding.

HIGHLIGHTS

- Maiden Ore Reserve of 34.5 Mt @ 0.65% Li₂O declared for Cinovec Project
- Richard Pavlik, current in-country manager, appointed as Director
- Short term funding secured

European Metals Managing Director Keith Coughlan said, "I am pleased to report a maiden Ore Reserve for Cinovec. The conversion of 34.5 million tonnes of Mineral Resource to Ore Reserve was facilitated by the recently published PFS. This is another significant step in the development of the largest lithium resource in Europe. I am also very pleased to welcome Richard Pavlik to the Board of Directors of European Metals on the resignation of Mr Pavel Reichl. Richard has made a significant contribution to the Company since taking the role of Country Manager in January and is a key component of the development of the project. On behalf of the Board I would like to thank Pavel for his role in the development of Cinovec to date. Pavel has been instrumental in securing the project and in managing a great deal of the early work. In addition, we have secured short term funding to allow us to continue work on the Definitive Feasibility Study whilst finalising discussions with a number of potential European based partners. It is the company's preferred route to partner with a European strategic investor for the bulk of the feasibility funding."

ORE RESERVE STATEMENT

Based upon the Preliminary Feasibility Study undertaken for the Cinovec Project, the Company declares a maiden Probable Ore Reserve of 34.5 Mt @ 0.65% Li₂O, as detailed below. The Probable Reserves have been declared solely from the Indicated Mineral Resource category and are classified based on a PFS level of study and category of Mineral Resource.

CINOVEC ORE RESERVES SUMMARY					
Category	Tonnes (Millions)	Li %	Li ₂ O %	Sn %	W %
Proven Ore Reserves	0	0	0	0	0
Probable Ore Reserves	34.5	0.30	0.65	0.09	0.03
Total Ore Reserves	34.5	0.30	0.65	0.09	0.03

Notes to Reserves Table.

1. Probable Ore Reserves have been prepared by Bara International in accordance with the guidelines of the JORC Code (2012).

2. The effective date of the Probable Ore Reserves is June 2017.

3. All figures are rounded to reflect the relative accuracy of the estimate.
4. The operator of the project is Geomet S.R.O. a wholly-owned subsidiary of EMH. Gross and Net Attributable Probable Ore Reserves are the same.
5. Any apparent inconsistencies are due to rounding errors.

The Mineral Resource for the Cinovec deposit was prepared by Widenbar and Associates and issued in February, 2017. The Mineral Resource is reported in the report Cinovec Resource Estimation published by Widenbar and Associates and is reported in accordance with the JORC 2012 guidelines. The table below summarises the Mineral Resource declared.

CINOVEC 2017 RESOURCE						
	Cutoff	Tonnes	Li	Li₂O	Sn	W
	%	(Millions)	%	%	%	%
INDICATED	0.1%	347.7	0.21	0.45	0.04	0.015
INFERRED	0.1%	308.8	0.18	0.39	0.04	0.014
TOTAL	0.1%	656.5	0.20	0.43	0.04	0.014

BOARD CHANGES

The Company is pleased to announce that Mr Richard Pavlik has been appointed to the Board with immediate effect. Mr Pavlik is the General Manager of Geomet s.r.o., the Company's wholly owned Czech subsidiary, and is a highly experienced Czech mining executive. Mr Pavlik holds a Masters Degree in Mining Engineer from the Technical University of Ostrava in Czech Republic. He is the former Chief Project Manager and Advisor to the Chief Executive Officer at OKD. OKD has been a major coal producer in the Czech Republic. He has almost 30 years of relevant industry experience in the Czech Republic. Mr Pavlik also has experience as a Project Analyst at Normandy Capital in Sydney as part of a postgraduate programme from Swinburne University. Mr Pavlik has held previous senior positions within OKD and New World Resources as Chief Engineer, and as Head of Surveying and Geology. He has also served as the Head of the Supervisory Board of NWR Karbonia, a Polish subsidiary of New World Resources (UK) Limited. He has an intimate knowledge of mining in the Czech Republic.

Mr Pavlik has been appointed to replace Mr. Pavel Reichl, who resigns on his request to pursue other interests. Mr Reichl has been instrumental in the development of the Cinovec Project and has been involved in the project since 2010. The company thanks Pavel for his vision in initially identifying the opportunity presented by the project and for his focused commitment in assisting in the development of the project to date. Mr Reichl will continue to provide geologic services on an as-needed basis.

INTERIM FUNDING

The Company is actively engaged in discussions with potential European strategic partners with regards to the funding and development of the Cinovec Project. Given the high level of interest in Europe in the lithium market, the Company is confident of a successful outcome in the near term in this regard. In order to allow sufficient time to finalise discussions and properly assess the various options open to the Company, the Company has arranged an interim funding facility to maintain momentum in developing the project.

This facility has been provided by an Australian based sophisticated investor, 6466 Investments Pty Ltd, and allows for the draw down of up to AUD 2 million in tranches as required over 12 months. Any funds drawn down will convert to CDI's in the Company at a 10% discount to the 10 day vwap in the Company's securities. The funds will be used in the preparation of the Company's Definitive Feasibility

Study, for further drilling and general working capital. The issue of shares pursuant to draw downs does not require shareholder approval.

BACKGROUND INFORMATION ON CINOVEC

PROJECT OVERVIEW

Cinovec Lithium/Tin Project

European Metals owns 100% of the Cinovec lithium-tin deposit in the Czech Republic. Cinovec is an historic mine incorporating a significant undeveloped lithium-tin resource with by-product potential including tungsten, rubidium, scandium, niobium and tantalum and potash. Cinovec hosts a globally significant hard rock lithium deposit with a total Indicated Mineral Resource of 348Mt @ 0.45% Li₂O and 0.04% Sn and an Inferred Mineral Resource of 309Mt @ 0.39% Li₂O and 0.04% Sn containing a combined 7.0 million tonnes Lithium Carbonate Equivalent and 263kt of tin.

This makes Cinovec the largest lithium deposit in Europe, the fourth largest non-brine deposit in the world and a globally significant tin resource.

The deposit has previously had over 400,000 tonnes of ore mined as a trial sub-level open stope underground mining operation.

The recently completed Preliminary Feasibility Study, conducted by specialist independent consultants, returned a post tax NPV of USD540m and an IRR of 21%. It confirmed the deposit is be amenable to bulk underground mining. Metallurgical test work has produced both battery grade lithium carbonate and high-grade tin concentrate at excellent recoveries. Cinovec is centrally located for European end-users and is well serviced by infrastructure, with a sealed road adjacent to the deposit, rail lines located 5 km north and 8 km south of the deposit and an active 22 kV transmission line running to the historic mine. As the deposit lies in an active mining region, it has strong community support.

The economic viability of Cinovec has been enhanced by the recent strong increase in demand for lithium globally, and within Europe specifically.

CONTACT

For further information on this update or the Company generally, please visit our website at www.europeanmet.com or contact:

Mr. Keith Coughlan
Managing Director

COMPETENT PERSON

Information in this release that relates to exploration results is based on information compiled by European Metals Director Dr Pavel Reichl. Dr Reichl is a Certified Professional Geologist (certified by the American Institute of Professional Geologists), a member of the American Institute of Professional Geologists, a Fellow of the Society of Economic Geologists and is a Competent Person as defined in the 2012 edition of the Australasian Code for Reporting of Exploration Results, Mineral Resources and Ore Reserves and a Qualified Person for the purposes of the AIM Guidance Note on Mining and Oil & Gas Companies dated June 2009. Dr Reichl consents to the inclusion in the release of the matters based on his information in the form and context in which it appears. Dr Reichl holds CDIs in European Metals.

The information in this release that relates to Mineral Resources and Exploration Targets has been compiled by Mr Lynn Widenbar. Mr Widenbar, who is a Member of the Australasian Institute of Mining and Metallurgy, is a full time employee of Widenbar and Associates and produced the estimate based on data and geological information supplied by European Metals. Mr Widenbar has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity that he is undertaking to qualify as a Competent Person as defined in the JORC Code 2012 Edition of the Australasian Code for Reporting of Exploration Results, Minerals Resources and Ore Reserves. Mr Widenbar consents to the inclusion in this report of the matters based on his information in the form and context that the information appears.

The information in this release that relates to Mineral Reserves is based on, and fairly represents, information and supporting documentation prepared by Mr Jim Pooley. Mr Pooley, who is a Fellow of the Southern African Institute of Mining and Metallurgy, is a full time employee of Bara International Ltd and produced the estimate based on the Mineral Resource supplied by European Metals. Mr Pooley has sufficient experience that is relevant to the style of mineralisation and type of deposit under consideration and to the activity that he is undertaking to qualify as a Competent Person as defined in the JORC Code 2012 Edition of the Australasian Code for Reporting of Exploration Results, Minerals Resources and Ore Reserves. Mr Pooley consents to the inclusion in this report of the matters based on his information in the form and context that the information appears.

CAUTION REGARDING FORWARD LOOKING STATEMENTS

Information included in this release constitutes forward-looking statements. Often, but not always, forward looking statements can generally be identified by the use of forward looking words such as “may”, “will”, “expect”, “intend”, “plan”, “estimate”, “anticipate”, “continue”, and “guidance”, or other similar words and may include, without limitation, statements regarding plans, strategies and objectives of management, anticipated production or construction commencement dates and expected costs or production outputs.

Forward looking statements inherently involve known and unknown risks, uncertainties and other factors that may cause the company’s actual results, performance and achievements to differ materially from any future results, performance or achievements. Relevant factors may include, but are not limited to, changes in commodity prices, foreign exchange fluctuations and general economic conditions, increased costs and demand for production inputs, the speculative nature of exploration and project development, including the risks of obtaining necessary licences and permits and diminishing quantities or grades of reserves, political and social risks, changes to the regulatory framework within which the company operates or may in the future operate, environmental conditions including extreme weather conditions, recruitment and retention of personnel, industrial relations issues and litigation.

Forward looking statements are based on the company and its management’s good faith assumptions relating to the financial, market, regulatory and other relevant environments that will exist and affect the company’s business and operations in the future. The company does not give any assurance that the assumptions on which forward looking statements are based will prove to be correct, or that the company’s business or operations will not be affected in any material manner by these or other factors not foreseen or foreseeable by the company or management or beyond the company’s control.

Although the company attempts and has attempted to identify factors that would cause actual actions, events or results to differ materially from those disclosed in forward looking statements, there may be other factors that could cause actual results, performance, achievements or events not to be as anticipated, estimated or intended, and many events are beyond the reasonable control of the company. Accordingly, readers are cautioned not to place undue reliance on forward looking statements. Forward looking statements in these materials speak only at the date of issue. Subject to any continuing obligations under applicable law or any relevant stock exchange listing rules, in

providing this information the company does not undertake any obligation to publicly update or revise any of the forward looking statements or to advise of any change in events, conditions or circumstances on which any such statement is based.

Statements regarding plans with respect to the Company’s mineral properties may contain forward-looking statements in relation to future matters that can only be made where the Company has a reasonable basis for making those statements.

This announcement has been prepared in compliance with the JORC Code 2012 Edition and the current ASX Listing Rules.

LITHIUM CLASSIFICATION AND CONVERSION FACTORS

Lithium grades are normally presented in percentages or parts per million (ppm). Grades of deposits are also expressed as lithium compounds in percentages, for example as a percent lithium oxide (Li₂O) content or percent lithium carbonate (Li₂CO₃) content.

Lithium carbonate equivalent (“LCE”) is the industry standard terminology for, and is equivalent to, Li₂CO₃. Use of LCE is to provide data comparable with industry reports and is the total equivalent amount of lithium carbonate, assuming the lithium content in the deposit is converted to lithium carbonate, using the conversion rates in the table included below to get an equivalent Li₂CO₃ value in percent. Use of LCE assumes 100% recovery and no process losses in the extraction of Li₂CO₃ from the deposit.

Lithium resources and reserves are usually presented in tonnes of LCE or Li.

The standard conversion factors are set out in the table below:

Table: Conversion Factors for Lithium Compounds and Minerals

Convert from		Convert to Li	Convert to Li ₂ O	Convert to Li ₂ CO ₃
Lithium	Li	1.000	2.153	5.324
Lithium Oxide	Li ₂ O	0.464	1.000	2.473
Lithium Carbonate	Li ₂ CO ₃	0.188	0.404	1.000

WEBSITE

A copy of this announcement is available from the Company’s website at www.europeanmet.com.

TECHNICAL GLOSSARY

The following is a summary of technical terms:

“beneficiation” or “benefication”	in extractive metallurgy, is any process that improves (benefits) the economic value of the ore by removing the gangue minerals, which results in a higher grade product (concentrate) and a waste stream (tailings)
“carbonate”	refers to a carbonate mineral such as calcite, CaCO ₃
“cut-off grade”	lowest grade of mineralised material considered economic, used in the calculation of Mineral Resources
“deposit”	coherent geological body such as a mineralised body

“exploration”	method by which ore deposits are evaluated
“g/t”	gram per metric tonne
“grade”	relative quantity or the percentage of ore mineral or metal content in an ore body
“Indicated” or “Indicated Mineral Resource”	as defined in the JORC and SAMREC Codes, is that part of a Mineral Resource which has been sampled by drill holes, underground openings or other sampling procedures at locations that are too widely spaced to ensure continuity but close enough to give a reasonable indication of continuity and where geoscientific data are known with a reasonable degree of reliability. An Indicated Mineral Resource will be based on more data and therefore will be more reliable than an Inferred Mineral Resource estimate
“Inferred” or “Inferred Mineral Resource”	as defined in the JORC and SAMREC Codes, is that part of a Mineral Resource for which the tonnage and grade and mineral content can be estimated with a low level of confidence. It is inferred from the geological evidence and has assumed but not verified geological and/or grade continuity. It is based on information gathered through the appropriate techniques from locations such as outcrops, trenches, pits, working and drill holes which may be limited or of uncertain quality and reliability
“JORC Code”	Joint Ore Reserve Committee Code; the Committee is convened under the auspices of the Australasian Institute of Mining and Metallurgy
“kt”	thousand tonnes
“LCE”	the total equivalent amount of lithium carbonate (see explanation above entitled Explanation of Lithium Classification and Conversion Factors)
“lithium”	a soft, silvery-white metallic element of the alkali group, the lightest of all metals
“lithium carbonate”	the lithium salt of carbonate with the formula Li_2CO_3
“Measured” or Measured Mineral Resources”	Measured: a mineral resource intersected and tested by drill holes, underground openings or other sampling procedures at locations which are spaced closely enough to confirm continuity and where geoscientific data are reliably known; a measured mineral resource estimate will be based on a substantial amount of reliable data, interpretation and evaluation which allows a clear determination to be made of shapes, sizes, densities and grades. Indicated: a mineral resource sampled by drill holes, underground openings or other sampling procedures at locations too widely spaced to ensure continuity but close enough to give a reasonable indication of continuity and where geoscientific data are known with a reasonable degree of reliability; an indicated resource will be based on more data, and therefore will be more reliable than an inferred resource estimate. Inferred: a mineral resource inferred from geoscientific evidence, underground openings or other sampling procedures where the lack of data is such that continuity cannot be predicted with confidence and where geoscientific data may not be known with a reasonable level of reliability
“metallurgical”	describing the science concerned with the production, purification and properties of metals and their applications
“micrometer”	(symbol μm) is an SI unit of length equal to one millionth of a metre
“Mineral Resource”	a concentration or occurrence of material of intrinsic economic interest in or on the Earth’s crust in such a form that there are reasonable prospects for the eventual economic extraction; the location, quantity, grade geological characteristics and continuity of a mineral resource are known, estimated or interpreted from specific geological evidence and knowledge; mineral resources are sub-divided into Inferred, Indicated and Measured categories

“mineralisation”	process of formation and concentration of elements and their chemical compounds within a mass or body of rock
“Mt”	million tonnes
“Ore Reserve”	An Ore Reserve is the economically mineable part of a Measured or Indicated Mineral Resource. It includes diluting materials and allowance for losses which may occur when the material is mined. Appropriate assessments, which may include pre-feasibility or feasibility studies, have been carried out, and will include consideration of an modification by realistically assumed mining, metallurgical, economic, marketing, legal, environmental, social and governmental factors. These assessments demonstrate at the time of reporting that extraction could reasonably be justified. Ore Reserves are sub-divided in order of increasing confidence into Probable Ore Reserves and Proved Ore Reserves.
“P80”	the mill circuit product size in micrometers
“ppm”	parts per million
“Probable Ore Reserve”	A Probable Ore Reserve is the economically mineable part of an Indicated Mineral Resource, and in some circumstances, Measured Mineral Resource.
“PSD”	particle size distribution
“recovery”	proportion of valuable material obtained in the processing of an ore, stated as a percentage of the material recovered compared with the total material present
“run-of-mine”	mined ore of a size that can be processed without further crushing
“semi-autogenous grinding” or “SAG”	a method of grinding rock into fine powder whereby the grinding media consist of larger chunks of rocks and steel balls
“stope”	underground excavation within the orebody where the main production takes place
“t”	a metric tonne
“tin”	A tetragonal mineral, rare; soft; malleable: bluish white, found chiefly in cassiterite, SnO ₂
“treatment”	Physical or chemical treatment to extract the valuable metals/minerals
“tungsten”	hard, brittle, white or grey metallic element. Chemical symbol, W; also known as wolfram
“W”	chemical symbol for tungsten

ADDITIONAL GEOLOGICAL TERMS

“apical”	relating to, or denoting an apex
“cassiterite”	a mineral, tin dioxide, SnO ₂ . Ore of tin with specific gravity 7
“cupola”	a dome-shaped projection at the top of an igneous intrusion
“dip”	the true dip of a plane is the angle it makes with the horizontal plane
“glaserite”	A colourless or white crystalline compound, K ₂ SO ₄ , used in glassmaking and fertilisers and as a reagent in analytical chemistry
“granite”	coarse-grained intrusive igneous rock dominated by light-coloured minerals, consisting of about 50% orthoclase, 25% quartz and balance of plagioclase feldspars and ferromagnesian silicates
“greisen”	a pneumatolithically altered granitic rock composed largely of quartz, mica, and topaz. The mica is usually muscovite or lepidolite. Tourmaline, fluorite, rutile, cassiterite, and wolframite are common accessory minerals
“igneous”	said of a rock or mineral that solidified from molten or partly molten material, i.e., from a magma
“muscovite”	also known as potash mica; formula: KAl ₂ (AlSi ₃ O ₁₀)(F,OH) ₂ .

“quartz”	a mineral composed of silicon dioxide, SiO ₂
“rhyolite”	an igneous, volcanic rock of felsic (silica rich) composition. Typically >69% SiO ₂
“vein”	a tabular deposit of minerals occupying a fracture, in which particles may grow away from the walls towards the middle
“wolframite”	a mineral, (Fe,Mn)WO ₄ ; within the huebnerite-ferberite series
“zinnwaldite”	a mineral, KLiFeAl(AlSi ₃)O ₁₀ (F,OH) ₂ ; mica group; basal cleavage; pale violet, yellowish or greyish brown; in granites, pegmatites, and greisens

ENQUIRIES:

European Metals Holdings Limited

Keith Coughlan, Chief Executive Officer

Tel: +61 (0) 419 996 333

Email: keith@europeanmet.com

Kiran Morzaria, Non-Executive Director

Tel: +44 (0) 20 7440 0647

Julia Beckett, Company Secretary

Tel: +61 (0) 6141 3504

Email: julia@europeanmet.com

Beaumont Cornish (Nomad & Broker)

Michael Cornish

Tel: +44 (0) 20 7628 3396

Roland Cornish

Email: corpfin@b-cornish.co.uk

The information contained within this announcement is considered to be inside information, for the purposes of Article 7 of EU Regulation 596/2014, prior to its release.

JORC Code, 2012 Edition - Table 1

Section 1 Sampling Techniques and Data

Criteria	JORC Code explanation	Commentary
Sampling techniques	<ul style="list-style-type: none"> Nature and quality of sampling (eg cut channels, random chips, or specific specialised industry standard measurement tools appropriate to the minerals under investigation, such as down hole gamma sondes, or handheld XRF instruments, etc). These examples should not be taken as limiting the broad meaning of sampling. Include reference to measures taken to ensure sample representivity and the appropriate calibration of any measurement tools or systems used. Aspects of the determination of mineralisation that are Material to the Public Report. In cases where ‘industry standard’ work has been done this would be relatively simple (eg ‘reverse circulation drilling was used to obtain 1 m samples from which 3 kg was pulverised to produce a 30 g charge for fire assay’). In other cases more explanation 	<ul style="list-style-type: none"> In 2014, the Company commenced a core drilling program and collected samples from core splits in line with JORC Code guidelines. Sample intervals honour geological or visible mineralization boundaries and vary between 50cm and 2 m. Majority of samples is 1 m in length The samples are half or quarter of core; the latter applied for large diameter core. Between 1952 and 1989, the Cinovec deposit was sampled in two ways: in drill core and underground channel samples. Channel samples, from drift ribs and faces, were collected during detailed exploration between 1952 and 1989 by Geindustria n.p. and Rudne Doly n.p., both Czechoslovak State companies.

Criteria	JORC Code explanation	Commentary
	<p><i>may be required, such as where there is coarse gold that has inherent sampling problems. Unusual commodities or mineralisation types (eg submarine nodules) may warrant disclosure of detailed information.</i></p>	<p>Sample length was 1 m, channel 10x5cm, sample mass about 15kg. Up to 1966, samples were collected using hammer and chisel; from 1966 a small drill (Holman Hammer) was used. 14179 samples were collected and transported to a crushing facility.</p> <ul style="list-style-type: none"> Core and channel samples were crushed in two steps: to -5mm, then to -0.5mm. 100g splits were obtained and pulverized to -0.045mm for analysis.
<p><i>Drilling techniques</i></p>	<ul style="list-style-type: none"> <i>Drill type (eg core, reverse circulation, open-hole hammer, rotary air blast, auger, Bangka, sonic, etc) and details (eg core diameter, triple or standard tube, depth of diamond tails, face-sampling bit or other type, whether core is oriented and if so, by what method, etc).</i> 	<ul style="list-style-type: none"> In 2014, three core holes were drilled for a total of 940.1m. In 2015, six core holes were drilled for a total of 2,455.0m. In 2016, eight core holes were drilled for a total of 2,795.6m. In 2014 and 2015, the core size was HQ3 (60mm diameter) in upper parts of holes; in deeper sections the core size was reduced to NQ3 (44mm diameter). Core recovery was high (average 98%). In 2016 up to four drill rigs were used, and select holes employed PQ sized core for upper parts of the drillholes. Historically only core drilling was employed, either from surface or from underground. Surface drilling: 80 holes, total 30,340 meters; vertical and inclined, maximum depth 1596m (structural hole). Core diameters from 220mm near surface to 110 mm at depth. Average core recovery 89.3%. Underground drilling: 766 holes for 53,126m; horizontal and inclined. Core diameter 46mm; drilled by Craelius XC42 or DIAMEC drills.
<p><i>Drill sample recovery</i></p>	<ul style="list-style-type: none"> <i>Method of recording and assessing core and chip sample recoveries and results assessed.</i> <i>Measures taken to maximise sample recovery and ensure representative nature of the samples.</i> <i>Whether a relationship exists between sample recovery and grade and whether sample bias may have occurred due to preferential loss/gain of fine/coarse material.</i> 	<ul style="list-style-type: none"> Core recovery for historical surface drill holes was recorded on drill logs and entered into the database. No correlation between grade and core recovery was established.
<p><i>Logging</i></p>	<ul style="list-style-type: none"> <i>Whether core and chip samples have been geologically and geotechnically logged to a level of detail to support appropriate Mineral Resource estimation, mining studies and metallurgical studies.</i> <i>Whether logging is qualitative or quantitative in nature. Core (or costean, channel, etc) photography.</i> 	<ul style="list-style-type: none"> In 2014-2016, core descriptions were recorded into paper logging forms by hand and later entered into an Excel database. Core was logged in detail historically in a facility 6 km from the mine site. The following features were logged and

Criteria	JORC Code explanation	Commentary
	<ul style="list-style-type: none"> <i>The total length and percentage of the relevant intersections logged.</i> 	<p>recorded in paper logs: lithology, alteration (including intensity divided into weak, medium and strong/pervasive), and occurrence of ore minerals expressed in %, macroscopic description of congruous intervals and structures and core recovery.</p>
<p><i>Sub-sampling techniques and sample preparation</i></p>	<ul style="list-style-type: none"> <i>If core, whether cut or sawn and whether quarter, half or all core taken.</i> <i>If non-core, whether riffled, tube sampled, rotary split, etc and whether sampled wet or dry.</i> <i>For all sample types, the nature, quality and appropriateness of the sample preparation technique.</i> <i>Quality control procedures adopted for all sub-sampling stages to maximise representivity of samples.</i> <i>Measures taken to ensure that the sampling is representative of the in situ material collected, including for instance results for field duplicate/second-half sampling.</i> <i>Whether sample sizes are appropriate to the grain size of the material being sampled.</i> 	<ul style="list-style-type: none"> In 2014-16, core was washed, geologically logged, sample intervals determined and marked then the core was cut in half. In 2016 larger core was cut in half and one half was cut again to obtain a quarter core sample. One half or one quarter samples was delivered to ALS Global for assaying after duplicates, blanks and standards were inserted in the sample stream. The remaining drill core is stored on site for reference. Sample preparation was carried out by ALS Global in Romania, using industry standard techniques appropriate for the style of mineralisation represented at Cinovec. Historically, core was either split or consumed entirely for analyses. Samples are considered to be representative. Sample size and grains size are deemed appropriate for the analytical techniques used.
<p><i>Quality of assay data and laboratory tests</i></p>	<ul style="list-style-type: none"> <i>The nature, quality and appropriateness of the assaying and laboratory procedures used and whether the technique is considered partial or total.</i> <i>For geophysical tools, spectrometers, handheld XRF instruments, etc, the parameters used in determining the analysis including instrument make and model, reading times, calibrations factors applied and their derivation, etc.</i> <i>Nature of quality control procedures adopted (eg standards, blanks, duplicates, external laboratory checks) and whether acceptable levels of accuracy (ie lack of bias) and precision have been established.</i> 	<ul style="list-style-type: none"> In 2014-16, core samples were assayed by ALS Global. The most appropriate analytical methods were determined by results of tests for various analytical techniques. The following analytical methods were chosen: ME-MS81 (lithium borate fusion or 4 acid digest, ICP-MS finish) for a suite of elements including Sn and W and ME-4ACD81 (4 acid digest, ICP-AES finish) additional elements including lithium. About 40% of samples were analysed by ME-MS81d (ME-MS81 plus whole rock package). Samples with over 1% tin are analysed by XRF. Samples over 1% lithium were analysed by Li-OG63 (four acid and ICP finish). Standards, blanks and duplicates were inserted into the sample stream. Initial tin standard results indicated possible downgrading bias; the laboratory repeated the analysis with satisfactory results. Historically, tin content was measured

Criteria	JORC Code explanation	Commentary
		<p>by XRF and using wet chemical methods. W and Li were analysed by spectral methods.</p> <ul style="list-style-type: none"> Analytical QA was internal and external. The former subjected 5% of the sample to repeat analysis in the same facility. 10% of samples were analysed in another laboratory, also located in Czechoslovakia. The QA/QC procedures were set to the State norms and are considered adequate. It is unknown whether external standards or sample duplicates were used. Overall accuracy of sampling and assaying was proved later by test mining and reconciliation of mined and analysed grades.
<p><i>Verification of sampling and assaying</i></p>	<ul style="list-style-type: none"> <i>The verification of significant intersections by either independent or alternative company personnel.</i> <i>The use of twinned holes.</i> <i>Documentation of primary data, data entry procedures, data verification, data storage (physical and electronic) protocols.</i> <i>Discuss any adjustment to assay data.</i> 	<ul style="list-style-type: none"> During the 2014-16 drill campaigns the Company indirectly verified grades of tin and lithium by comparing the length and grade of mineral intercepts with the current block model.
<p><i>Location of data points</i></p>	<ul style="list-style-type: none"> <i>Accuracy and quality of surveys used to locate drill holes (collar and down-hole surveys), trenches, mine workings and other locations used in Mineral Resource estimation.</i> <i>Specification of the grid system used.</i> <i>Quality and adequacy of topographic control.</i> 	<ul style="list-style-type: none"> In 2014-16, drill collar locations were surveyed by a registered surveyor. Down hole surveys were recorded by a contractor. Historically, drill hole collars were surveyed with a great degree of precision by the mine survey crew. Hole locations are recorded in the local S-JTSK Krovak grid. Topographic control is excellent.
<p><i>Data spacing and distribution</i></p>	<ul style="list-style-type: none"> <i>Data spacing for reporting of Exploration Results.</i> <i>Whether the data spacing and distribution is sufficient to establish the degree of geological and grade continuity appropriate for the Mineral Resource and Ore Reserve estimation procedure(s) and classifications applied.</i> <i>Whether sample compositing has been applied.</i> 	<ul style="list-style-type: none"> Historical data density is very high. Spacing is sufficient to establish an inferred resource that was initially estimated using MICROMINE software in Perth, 2012. Areas with lower coverage of Li% assays have been identified as exploration targets. Sample compositing to 1m intervals has been applied mathematically prior to estimation but not physically.
<p><i>Orientation of data in relation to geological structure</i></p>	<ul style="list-style-type: none"> <i>Whether the orientation of sampling achieves unbiased sampling of possible structures and the extent to which this is known, considering the deposit type.</i> <i>If the relationship between the drilling orientation and the orientation of key mineralised structures is considered to have introduced a sampling bias, this should be</i> 	<ul style="list-style-type: none"> In 2014-16, drill hole azimuth and dip was planned to intercept the mineralized zones at near-true thickness. As the mineralized zones dip shallowly to the south, drill holes were vertical or near vertical and directed to the north. Due to land access restrictions, certain holes could not be positioned in sites with

Criteria	JORC Code explanation	Commentary
	<i>assessed and reported if material.</i>	<p>ideal drill angle.</p> <ul style="list-style-type: none"> The Company has not directly collected any samples underground because the workings are inaccessible at this time. Based on historic reports, level plan maps, sections and core logs, the samples were collected in an unbiased fashion, systematically on two underground levels from drift ribs and faces, as well as from underground holes drilled perpendicular to the drift directions. The sample density is adequate for the style of deposit. Multiple samples were taken and analysed by the Company from the historic tailing repository. Only lithium was analysed (Sn and W too low). The results matched the historic grades.
<i>Sample security</i>	<ul style="list-style-type: none"> <i>The measures taken to ensure sample security.</i> 	<ul style="list-style-type: none"> In the 2014-16 programs, only the Company's employees and contractors handled drill core and conducted sampling. The core was collected from the drill rig each day and transported in a company vehicle to the secure Company premises where it was logged and cut. Company geologists supervised the process and logged/sampled the core. The samples were transported by Company personnel in a Company vehicle to the ALS Global laboratory pick-up station. The remaining core is stored under lock and key. Historically, sample security was ensured by State norms applied to exploration. The State norms were similar to currently accepted best practice and JORC guidelines for sample security.
<i>Audits or reviews</i>	<ul style="list-style-type: none"> <i>The results of any audits or reviews of sampling techniques and data.</i> 	<ul style="list-style-type: none"> Review of sampling techniques possible from written records. No flaws found.

Section 2 Reporting of Exploration Results

Criteria	JORC Code explanation	Commentary
<i>Mineral tenement and land tenure status</i>	<ul style="list-style-type: none"> <i>Type, reference name/number, location and ownership including agreements or material issues with third parties such as joint ventures, partnerships, overriding royalties, native title interests, historical sites, wilderness or national park and environmental settings.</i> <i>The security of the tenure held at the time of reporting along with any known impediments to obtaining a</i> 	<ul style="list-style-type: none"> Cinovec exploration rights held under three licenses Cinovec (expires 30/07/2019), Cinovec 2 (expires 31/12/2020) and Cinovec 3 (expires 31/10/2021). 100% owned, no native interests or environmental concerns. A State royalty applies metals production and is set as a fee in Czech crowns per unit of metal produced. There are no known impediments to

Criteria	JORC Code explanation	Commentary
	<i>licence to operate in the area.</i>	obtaining an Exploitation Permit for the defined resource.
<i>Exploration done by other parties</i>	<ul style="list-style-type: none"> <i>Acknowledgment and appraisal of exploration by other parties.</i> 	<ul style="list-style-type: none"> There has been no acknowledgment or appraisal of exploration by other parties.
<i>Geology</i>	<ul style="list-style-type: none"> <i>Deposit type, geological setting and style of mineralisation.</i> 	<ul style="list-style-type: none"> Cinovec is a granite-hosted tin-tungsten-lithium deposit. Late Variscan age, post-orogenic granite intrusion Tin and tungsten occur in oxide minerals (cassiterite and wolframite). Lithium occurs in zinwaldite, a Li-rich muscovite Mineralization in a small granite cupola. Vein and greisen type. Alteration is greisenisation, silicification.
<i>Drill hole Information</i>	<ul style="list-style-type: none"> <i>A summary of all information material to the understanding of the exploration results including a tabulation of the following information for all Material drill holes:</i> <ul style="list-style-type: none"> <i>easting and northing of the drill hole collar</i> <i>elevation or RL (Reduced Level – elevation above sea level in metres) of the drill hole collar</i> <i>dip and azimuth of the hole</i> <i>down hole length and interception depth</i> <i>hole length.</i> <i>If the exclusion of this information is justified on the basis that the information is not Material and this exclusion does not detract from the understanding of the report, the Competent Person should clearly explain why this is the case.</i> 	<ul style="list-style-type: none"> Reported previously.
<i>Data aggregation methods</i>	<ul style="list-style-type: none"> <i>In reporting Exploration Results, weighting averaging techniques, maximum and/or minimum grade truncations (eg cutting of high grades) and cut-off grades are usually Material and should be stated.</i> <i>Where aggregate intercepts incorporate short lengths of high grade results and longer lengths of low grade results, the procedure used for such aggregation should be stated and some typical examples of such aggregations should be shown in detail.</i> <i>The assumptions used for any reporting of metal equivalent values should be clearly stated.</i> 	<ul style="list-style-type: none"> Reporting of exploration results has not and will not include aggregate intercepts. Metal equivalent not used in reporting. No grade truncations applied.
<i>Relationship between mineralisation</i>	<ul style="list-style-type: none"> <i>These relationships are particularly important in the reporting of Exploration Results.</i> <i>If the geometry of the mineralisation</i> 	<ul style="list-style-type: none"> Intercept widths are approximate true widths. The mineralization is mostly of disseminated nature and relatively

Criteria	JORC Code explanation	Commentary
<i>widths and intercept lengths</i>	<p><i>with respect to the drill hole angle is known, its nature should be reported.</i></p> <ul style="list-style-type: none"> <i>If it is not known and only the down hole lengths are reported, there should be a clear statement to this effect (eg 'down hole length, true width not known').</i> 	<p>homogeneous; the orientation of samples is of limited impact.</p> <ul style="list-style-type: none"> For higher grade veins care was taken to drill at angles ensuring closeness of intercept length and true widths The block model accounts for variations between apparent and true dip.
<i>Diagrams</i>	<ul style="list-style-type: none"> <i>Appropriate maps and sections (with scales) and tabulations of intercepts should be included for any significant discovery being reported These should include, but not be limited to a plan view of drill hole collar locations and appropriate sectional views.</i> 	<ul style="list-style-type: none"> Appropriate maps and sections have been generated by the Company, and independent consultants. Available in customary vector and raster outputs, and partially in consultant's reports.
<i>Balanced reporting</i>	<ul style="list-style-type: none"> <i>Where comprehensive reporting of all Exploration Results is not practicable, representative reporting of both low and high grades and/or widths should be practiced to avoid misleading reporting of Exploration Results.</i> 	<ul style="list-style-type: none"> Balanced reporting in historic reports guaranteed by norms and standards, verified in 1997, and 2012 by independent consultants. The historic reporting was completed by several State institutions and cross validated.
<i>Other substantive exploration data</i>	<ul style="list-style-type: none"> <i>Other exploration data, if meaningful and material, should be reported including (but not limited to): geological observations; geophysical survey results; geochemical survey results; bulk samples – size and method of treatment; metallurgical test results; bulk density, groundwater, geotechnical and rock characteristics; potential deleterious or contaminating substances.</i> 	<ul style="list-style-type: none"> Data available: bulk density for all representative rock and ore types; (historic data + 92 measurements in 2016 from current core holes); petrographic and mineralogical studies, hydrological information, hardness, moisture content, fragmentation etc.
<i>Further work</i>	<ul style="list-style-type: none"> <i>The nature and scale of planned further work (eg tests for lateral extensions or depth extensions or large-scale step-out drilling).</i> <i>Diagrams clearly highlighting the areas of possible extensions, including the main geological interpretations and future drilling areas, provided this information is not commercially sensitive.</i> 	<ul style="list-style-type: none"> Grade verification sampling from underground or drilling from surface. Historically-reported grades require modern validation in order to improve the resource classification. The number and location of sampling sites will be determined from a 3D wireframe model and geostatistical considerations reflecting grade continuity. The geologic model will be used to determine if any infill drilling is required. The deposit is open down-dip on the southern extension, and locally poorly constrained at its western and eastern extensions, where limited additional drilling might be required. No large scale drilling campaigns are required.

Section 3 Estimation and Reporting of Mineral Resources

Criteria	JORC Code explanation	Commentary
Database integrity	<ul style="list-style-type: none"> Measures taken to ensure that data has not been corrupted by, for example, transcription or keying errors, between its initial collection and its use for Mineral Resource estimation purposes. Data validation procedures used. 	<ul style="list-style-type: none"> Assay and geologic data were compiled by the Company staff from primary historic records, such as copies of drill logs and large scale sample location maps. Sample data were entered in to Excel spreadsheets by Company staff in Prague. The database entry process was supervised by a Professional Geologist who works for the Company. The database was checked by independent competent persons (Lynn Widenbar of Widenbar & Associates, Phil Newell of Wardell Armstrong International).
Site visits	<ul style="list-style-type: none"> Comment on any site visits undertaken by the Competent Person and the outcome of those visits. If no site visits have been undertaken indicate why this is the case. 	<ul style="list-style-type: none"> The site was visited by Mr Pavel Reichl who has identified the previous shaft sites, tails dams and observed the mineralisation underground through an adjacent mine working. The site was visited in June 2016 by Mr Lynn Widenbar, the Competent Person for Mineral Resource Estimation. Diamond drill rigs were viewed, as was core; a visit was carried out to the adjacent underground mine in Germany which is a continuation of the Cinovec Deposit.
Geological interpretation	<ul style="list-style-type: none"> Confidence in (or conversely, the uncertainty of) the geological interpretation of the mineral deposit. Nature of the data used and of any assumptions made. The effect, if any, of alternative interpretations on Mineral Resource estimation. The use of geology in guiding and controlling Mineral Resource estimation. The factors affecting continuity both of grade and geology. 	<ul style="list-style-type: none"> The overall geology of the deposit is relatively simple and well understood due to excellent data control from surface and underground. Nature of data: underground mapping, structural measurements, detailed core logging, 3D data synthesis on plans and maps. Geological continuity is good. The grade is highest and shows most variability in quartz veins. Grade correlates with degree of silicification and greisenisation of the host granite. The primary control is the granite-country rock contact. All mineralization is in the uppermost 200m of the granite and is truncated by the contact.
Dimensions	<ul style="list-style-type: none"> The extent and variability of the Mineral Resource expressed as length (along strike or otherwise), plan width, and depth below surface to the upper and lower limits of the Mineral Resource. 	<ul style="list-style-type: none"> The Cinovec South deposit strikes north-south, is elongated, and dips gently south parallel to the upper granite contact. The surface projection of mineralization is about 1 km long and

Criteria	JORC Code explanation	Commentary
<i>Estimation and modelling techniques</i>	<ul style="list-style-type: none"> • <i>The nature and appropriateness of the estimation technique(s) applied and key assumptions, including treatment of extreme grade values, domaining, interpolation parameters and maximum distance of extrapolation from data points. If a computer assisted estimation method was chosen include a description of computer software and parameters used.</i> • <i>The availability of check estimates, previous estimates and/or mine production records and whether the Mineral Resource estimate takes appropriate account of such data.</i> • <i>The assumptions made regarding recovery of by-products.</i> • <i>Estimation of deleterious elements or other non-grade variables of economic significance (eg sulphur for acid mine drainage characterisation).</i> • <i>In the case of block model interpolation, the block size in relation to the average sample spacing and the search employed.</i> • <i>Any assumptions behind modelling of selective mining units.</i> • <i>Any assumptions about correlation between variables.</i> • <i>Description of how the geological interpretation was used to control the resource estimates.</i> • <i>Discussion of basis for using or not using grade cutting or capping.</i> • <i>The process of validation, the checking process used, the comparison of model data to drill hole data, and use of reconciliation data if available.</i> 	<p>900 m wide.</p> <ul style="list-style-type: none"> • Mineralization extends from about 200m to 500m below surface. <ul style="list-style-type: none"> • Block estimation was carried out in Micromine using Ordinary Kriging interpolation. • A geological domain model was constructed using Leapfrog software with solid wireframes representing greisen, granite, greisenised granite and the overlying barren rhyolite. This was used to both control interpolation and to assign density to the model (2.57 for granite, 2.70 for greisen and 2.60 for all other material). • Analysis of sample lengths indicated that compositing to 1m was necessary. • Search ellipse sizes and orientations for the estimation were based on drill hole spacing, the known orientations of mineralisation and variography. • An “unfolding” search strategy was used which allowed the search ellipse orientation to vary with the locally changing dip and strike. • After statistical analysis, a top cut of 5% was applied to Sn% and W%; no top cut is applied to Li%. • Sn% and Li% were then estimated by Ordinary Kriging within the mineralisation solids. • The primary search ellipse was 150m along strike, 150m down dip and 7.5m across the mineralisation. A minimum of 4 composites and a maximum of 8 composites were required. • A second interpolation with search ellipse of 300m x 300m x 12.5m was carried out to inform blocks to be used as the basis for an exploration target. • Block size was 5m (E-W) by 10m (N-S) by 5m • Validation of the final resource has been carried out in a number of ways including section comparison of data versus model, swathe plots and production reconciliation.
<i>Moisture</i>	<ul style="list-style-type: none"> • <i>Whether the tonnages are estimated on a dry basis or with natural moisture, and the method of determination of the moisture content.</i> 	<ul style="list-style-type: none"> • Tonnages are estimated on a dry basis using the average bulk density for each geological domain.
<i>Cut-off parameters</i>	<ul style="list-style-type: none"> • <i>The basis of the adopted cut-off grade(s) or quality parameters applied.</i> 	<ul style="list-style-type: none"> • A series of alternative cutoffs was used to report tonnage and grade: Sn 0.1%, 0.2%, 0.3% and 0.4%. Lithium 0.1%,

Criteria	JORC Code explanation	Commentary
<i>Mining factors or assumptions</i>	<ul style="list-style-type: none"> Assumptions made regarding possible mining methods, minimum mining dimensions and internal (or, if applicable, external) mining dilution. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential mining methods, but the assumptions made regarding mining methods and parameters when estimating Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the mining assumptions made. 	<p>0.2%, 0.3% and 0.4%.</p> <ul style="list-style-type: none"> Mining is assumed to be by underground methods. A Scoping Study has determined the optimal mining method. Limited internal waste will need to be mined at grades marginally below cutoffs. Mine dilution and waste are expected at minimal levels and the vast majority of the Mineral Resource is expected to convert to an Ore Reserve. Based on the geometry of the deposit, it is envisaged that a combination of drift and fill mining and longhole open stoping will be used.
<i>Metallurgical factors or assumptions</i>	<ul style="list-style-type: none"> The basis for assumptions or predictions regarding metallurgical amenability. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider potential metallurgical methods, but the assumptions regarding metallurgical treatment processes and parameters made when reporting Mineral Resources may not always be rigorous. Where this is the case, this should be reported with an explanation of the basis of the metallurgical assumptions made. 	<ul style="list-style-type: none"> Recent testwork on 2014 drill core indicates a tin recovery of 80% can be expected. Testwork on lithium is complete, with 70% recovery of lithium to lithium carbonate product via flotation concentrate and atmospheric leach. Extensive testwork was conducted on Cinovec South ore in the past. Testing culminated with a pilot plant trial in 1970, where three batches of Cinovec South ore were processed, each under slightly different conditions. The best result, with a tin recovery of 76.36%, was obtained from a batch of 97.13t grading 0.32% Sn. A more elaborate flowsheet was also investigated and with flotation produced final Sn and W recoveries of better than 96% and 84%, respectively. Historical laboratory testwork demonstrated that lithium can be extracted from the ore (lithium carbonate was produced from 1958-1966 at Cinovec).
<i>Environmental factors or assumptions</i>	<ul style="list-style-type: none"> Assumptions made regarding possible waste and process residue disposal options. It is always necessary as part of the process of determining reasonable prospects for eventual economic extraction to consider the potential environmental impacts of the mining and processing operation. While at this stage the determination of potential environmental impacts, particularly for a greenfields project, may not always be well advanced, the status of early consideration of these potential environmental impacts should be reported. Where these aspects have not 	<ul style="list-style-type: none"> Cinovec is in an area of historic mining activity spanning the past 600 years. Extensive State exploration was conducted until 1990. The property is located in a sparsely populated area, most of the land belongs to the State. Few problems are anticipated with regards to the acquisition of surface rights for any potential underground mining operation. The envisaged mining method will see much of the waste and tailings used as

Criteria	JORC Code explanation	Commentary
	<p><i>been considered this should be reported with an explanation of the environmental assumptions made.</i></p>	<p>underground fill.</p>
<p><i>Bulk density</i></p>	<ul style="list-style-type: none"> • <i>Whether assumed or determined. If assumed, the basis for the assumptions. If determined, the method used, whether wet or dry, the frequency of the measurements, the nature, size and representativeness of the samples.</i> • <i>The bulk density for bulk material must have been measured by methods that adequately account for void spaces (vugs, porosity, etc), moisture and differences between rock and alteration zones within the deposit.</i> • <i>Discuss assumptions for bulk density estimates used in the evaluation process of the different materials.</i> 	<ul style="list-style-type: none"> • Historical bulk density measurements were made in a laboratory. • The following densities were applied: <ul style="list-style-type: none"> ○ 2.57 for granite ○ 2.70 for greisen ○ 2.60 for all other material
<p><i>Classification</i></p>	<ul style="list-style-type: none"> • <i>The basis for the classification of the Mineral Resources into varying confidence categories.</i> • <i>Whether appropriate account has been taken of all relevant factors (ie relative confidence in tonnage/grade estimations, reliability of input data, confidence in continuity of geology and metal values, quality, quantity and distribution of the data).</i> • <i>Whether the result appropriately reflects the Competent Person's view of the deposit.</i> 	<ul style="list-style-type: none"> • Following a review of a small amount of available QAQC data, and comparison of production data versus estimated tonnage/grade from the resource model, and given the close spacing of underground drilling and development, the majority of the Tin resource was originally classified in the Inferred category as defined by the 2012 edition of the JORC code. • The new 2014 and 2016 drilling has confirmed the Tin mineralisation model and a part of this area has been upgraded to the Indicated category. • The Li% mineralisation has been assigned to the Inferred category where the average distance to composites used in estimation is less than 100m. Material outside this range is unclassified but has been used as the basis for an Exploration Target. • The new 2014 and 2016 drilling has confirmed the Lithium mineralisation model and a part of this area has been upgraded to the Indicated category. • The Competent Person (Lynn Widenbar) endorses the final results and classification.
<p><i>Audits or reviews</i></p>	<ul style="list-style-type: none"> • <i>The results of any audits or reviews of Mineral Resource estimates.</i> 	<ul style="list-style-type: none"> • Wardell Armstrong International, in their review of Lynn Widenbar's initial resource estimate stated "the Widenbar model appears to have been prepared in a diligent manner and given the data available provides a reasonable estimate of the drillhole assay data at the Cinovec deposit".

Criteria	JORC Code explanation	Commentary
Discussion of relative accuracy/confidence	<ul style="list-style-type: none"> Where appropriate a statement of the relative accuracy and confidence level in the Mineral Resource estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the resource within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors that could affect the relative accuracy and confidence of the estimate. The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used. These statements of relative accuracy and confidence of the estimate should be compared with production data, where available. 	<ul style="list-style-type: none"> In 2012, WAI carried out model validation exercises on the initial Widenbar model, which included visual comparison of drilling sample grades and the estimated block model grades, and Swath plots to assess spatial local grade variability. A visual comparison of Block model grades vs drillhole grades was carried out on a sectional basis for both Sn and Li mineralisation. Visually, grades in the block model correlated well with drillhole grade for both Sn and Li. Swathe plots were generated from the model by averaging composites and blocks in all 3 dimensions using 10m panels. Swathe plots were generated for the Sn and Li estimated grades in the block model, these should exhibit a close relationship to the composite data upon which the estimation is based. As the original drillhole composites were not available to WAI. 1m composite samples based on 0.1% cut-offs for both Sn and Li assays were Overall Swathe plots illustrate a good correlation between the composites and the block grades. As is visible in the Swathe plots, there has been a large amount of smoothing of the block model grades when compared to the composite grades, this is typical of the estimation method.

ORE as at 1ST JUNE 2017

Section 4 Estimation and Reporting of Ore Reserves

(Criteria listed in section 1, and where relevant in section 2 and 3, also apply to this section.)

Criteria	JORC Code explanation	Commentary				
Mineral Resource estimate for conversion to Ore reserves	<ul style="list-style-type: none"> Description of the Mineral Resource estimate used as a basis for the conversion to an Ore Reserve. Clear statement as to whether the Mineral Resources are reported additional to, or inclusive of, the Ore Reserves. 	<p>A JORC 2012 Mineral Resource Estimate (MRE) was issued by Widenbar and Associates. The electronic resource models were provided to Bara for the purposes of mine design.</p> <p>The table below summarises the mineral resource provided.</p>				
CINOVEC 2017 RESOURCE						
	Cutoff	Tonnes	Li	Li₂O	Sn	W
	%	(Millions)	%	%	%	%
INDICATED	0.1%	347.7	0.21	0.45	0.04	0.015
INFERRED	0.1%	308.8	0.18	0.39	0.04	0.014
TOTAL	0.1%	656.5	0.20	0.43	0.04	0.014

Criteria	JORC Code explanation	Commentary
Site visits	<ul style="list-style-type: none"> • <i>Comment on any site visits undertaken by the Competent Person and the outcome of those visits.</i> • <i>If no site visits have been undertaken indicate why this is the case.</i> 	<p>The Mineral Resources are declared inclusive of Ore Reserves.</p> <p>The CP visited the site on 7th and 8th of September 2016, inspections were made of:</p> <ul style="list-style-type: none"> ○ Exploration drill cores. ○ Underground visits were undertaken to old underground mine workings close to and situated in the same deposits as the Cinovec project area. ○ The project surface site was visited including visits to: <ul style="list-style-type: none"> ▪ Possible surface infrastructure sites. ▪ The sites of existing vertical shafts into the old Cinovec mine workings ▪ Access road and rail infrastructure.
Study Status	<ul style="list-style-type: none"> • <i>The type and level of study undertaken to enable Mineral Resources to be converted to Ore Reserves.</i> • <i>The Code requires that a study to at least Pre-Feasibility Study level has been undertaken to convert Mineral Resources to Ore Reserves. Such studies will have been carried out and will have determined a mine plan that is technically achievable and economically viable, and that material Modifying Factors have been considered.</i> 	<p>A pre-feasibility study (PFS) has been undertaken for the Cinovec Project. All material issues relevant to the project have been considered in this study to ensure estimates to levels of accuracy generally accepted for a PFS.</p>
Cut-off parameters	<ul style="list-style-type: none"> • <i>The basis of the cut-off grade(s) or quality parameters applied.</i> 	<p>Revenue will be generated from the sales of Lithium (Li), Tin (Sn) and Tungsten (W). Each metal has different in-situ grades, plant recoveries, operating costs and metal prices. To determine the revenue generated from a block of material in the block model there factors need to be taken into account. To do this the total revenue and operating costs were calculated using a script in the block model. The cost was deducted from the revenue to produce a “Margin” value for each block. Where Margin is greater than zero, the block is flagged as ore. The metal prices, recoveries and formulae used to calculate the operating costs for purposes of the margin calculation are tabled below.</p> <p><i>(Please refer to the announcement on the European Metals Website for the Table described above – www.europeanmet.com.)</i></p>
		<p>Using the factors tabled above the “Margin” value was calculated for each block in the block model. The breakeven grade is where Margin =0. All blocks with Margin greater than zero could be considered ore. Applying this criteria to the block model allowed a grade versus tonnage curve to be generated based on using the “Margin” field as the</p>

Criteria	JORC Code explanation	Commentary
		<p>grade field. The resultant curve is shown in the Figure below.</p> <p><i>(Please refer to the announcement on the European Metals Website for the Table described above – www.europeanmet.com.)</i></p> <p>In order to optimise the value of the project a strategic decision was made by the client to mine at a higher grade than the average and to optimise the mined grade by reducing the tonnes and increasing the grade to the point where mine life becomes the constraint, or the mining becomes prohibitively selective. The production rate of the processing plant was set by EMH at 360,000 tpa of mica concentrate. This equates to approximately 1.7 million tpa of RoM ore. For a mine life of over 20 years, which was the requirement stated by EM, the mining inventory needs to be at least 34 million tonnes. Using the grade versus tonnage curve a cut-off of US\$35/tonne Margin was selected. This resulted in the appropriate mine life while still allowing the use of bulk mining methods such as LHOS.</p>
<p><i>Mining factors or assumptions</i></p>	<ul style="list-style-type: none"> • <i>The method and assumptions used as reported in the Pre-Feasibility or Feasibility Study to convert the Mineral Resource to an Ore Reserve (i.e. either by application of appropriate factors by optimisation or by preliminary or detailed design).</i> • <i>The choice, nature and appropriateness of the selected mining method(s) and other mining parameters including associated design issues such as pre-strip, access, etc.</i> • <i>The assumptions made regarding geotechnical parameters (eg pit slopes, stope sizes, etc), grade control and pre-production drilling.</i> • <i>The major assumptions made and Mineral Resource model used for pit and stope optimisation (if appropriate).</i> • <i>The mining dilution factors used.</i> • <i>The mining recovery factors used.</i> • <i>Any minimum mining widths used.</i> • <i>The manner in which Inferred Mineral Resources are utilised in mining studies and the sensitivity of the outcome to their inclusion.</i> • <i>The infrastructure requirements of the selected mining methods.</i> 	<p><u>Geotechnical input</u></p> <p>A geotechnical study was completed as part of the pre-feasibility study. The geotechnical study prescribed geotechnical design criteria which should be applied in the mine design. The design criteria are detailed in the table below.</p> <p><i>(Please refer to the announcement on the European Metals Website for the Table described above – www.europeanmet.com.)</i></p> <p><u>Block model</u></p> <p>The block model file used for this study was provided to Bara by EM in February 2017 and is entitled Cinovec_Resource_Model_17_02_2017.dm. The model is in Datamine format. The table below</p>

Criteria	JORC Code explanation	Commentary
		<p>shows the fields in the block model that were used in the mine planning process.</p> <p><i>(Please refer to the announcement on the European Metals Website for the Table described above – www.europeanmet.com.)</i></p>
		<p><u>Mining method</u></p> <p>An evaluation was completed to establish the achievable extraction ratios with and without backfill, based on the geotechnical design criteria including pillar sizes and stope spans (see above). The preferred option was to mine with pillars support only, negating the requirement for a backfill plant.</p> <p>The selected mining method is long hole open stoping with pillar support. The payable ore will be split into blocks approximately 90 m long in the strike direction and 25 m high. The bottom of each block will be accessed in the central position by an access crosscut and the block will be mined out from the centre to the strike limit by drifting. The stope will be mined on retreat from the block extent, retreating to the access cross cut position. The stopes will be a maximum of 13 m wide with rib pillars between stopes of 4 to 7 m wide depending on stope height. Access to the stopes will be by footwall drives developed in the footwall at 25 m vertical intervals. All stope access crosscuts will be developed out of the footwall drives.</p> <p>The mine will be accessed by a twin decline system. A conveyor will be installed from the underground primary crusher on 590m Elevation to surface in the conveyor decline. The second decline will be used as a service decline for men, material and as an intake airway.</p> <p><u>Mining modifying factors</u></p> <p>Stope shapes were determined by use of stope optimisation software after application of minimum stope size and stope geometry. The design criteria specified included:</p> <ul style="list-style-type: none"> • Cut-off – Margin >US\$35 per tonne. This means that the average margin of the resultant stope shape must be greater than US\$35/tonne. • Stope width – 17 m (includes rib pillar, which was deducted as a tonnage loss later in the schedule) • Maximum stope height – Unlimited. Stope shapes greater than 25m high were later split

Criteria	JORC Code explanation	Commentary
		<p>by level and sill pillar losses accounted for.</p> <ul style="list-style-type: none"> • Minimum stope height – 5m (height of ore drive). • Stope length – Minimum 10 m, maximum unlimited. Stopes were later split into stope blocks with maximum length of 180 m (two stopes of 90 m each) • Minimum footwall slope angle - 50°. <p>After definition of the stope shapes mining modifying factors as described below were applied:</p> <p><i>Mining Exclusions</i></p> <ol style="list-style-type: none"> 1. The Northern most portion of the orebody is located below the village. In this area it was agreed to leave an unmined crown pillar of at least 150 m between surface and the uppermost mining level. In other parts of the orebody the crown pillar was 70 m. 2. DSO created stope shapes according to the criteria specified above, but with no consideration of the development required to access these blocks. The design was edited to remove any blocks that were not practical to access, being either excessively far from planned development and too small to justify the access development, or small volumes on an elevation that is difficult to access being between mining levels. <p><i>Pillar loss</i></p> <p>Total pillar loss is estimated to be 35%.</p> <p><i>Unplanned dilution</i></p> <p>In order to account for these mining inefficiencies unplanned dilution was added to all stope tonnage. Due to the large size of the stopes the dilution percentage is low at 3%. This allows for approximately 0.25 m of over break around the entire stope.</p> <p>Since the stopes are defined by a grade cut-off and the mineralisation is disseminated, there is not expected to be a sharp drop-off of grade outside the stope envelope. The dilution will therefore contain metal grade. The average grade of the resource below the margin cut-off of US\$35/t has been applied to the dilution material in the mine plan. The grade of the dilution is:</p> <p style="text-align: center;">Li% - 0.22</p>

Criteria	JORC Code explanation	Commentary
		<p data-bbox="1002 250 1120 277">Sn% - 0.04</p> <p data-bbox="1002 309 1120 336">W% - 0.01</p> <p data-bbox="1002 367 1094 394"><i>Ore loss</i></p> <p data-bbox="906 425 1430 519">Ore loss does occur in mining operations due to mining inefficiencies. This can be due to factors such as:</p> <ul data-bbox="906 551 1362 716" style="list-style-type: none"> <li data-bbox="906 551 1273 577">• Ore not loaded out of stopes <li data-bbox="906 586 1181 613">• Grade control errors <li data-bbox="906 622 1120 649">• Haulage errors <li data-bbox="906 658 1362 685">• Underbreak in the blasting operation <li data-bbox="906 694 1126 721">• Stope hang ups <p data-bbox="906 752 1414 882">To account for these inefficiencies an ore loss factor of 3% has been included in the mining schedule. This is a tonnage loss at the average grade of the block.</p> <p data-bbox="906 913 1117 940"><u>Inferred Resources</u></p> <p data-bbox="906 972 1458 1066">No inferred resources were included as ore in the pre-feasibility mine plan. Inferred resources were treated as waste.</p> <p data-bbox="906 1097 1062 1124"><u>Infrastructure</u></p> <p data-bbox="906 1155 1145 1182"><i>Surface Infrastructure</i></p> <p data-bbox="906 1214 1471 1500">The surface infrastructure has been designed to support the mining plan with consideration of the labour and mechanised equipment requirements of the operation in addition to the movement of rock, men and materials. The infrastructure is divided into two distinct areas, with the area at the portal servicing the initial development requirements and the second servicing the production phase. Allowance has been made for;</p> <ul data-bbox="906 1532 1407 2060" style="list-style-type: none"> <li data-bbox="906 1532 1139 1559">• Security fencing. <li data-bbox="906 1568 1299 1594">• Site access control and parking. <li data-bbox="906 1603 1184 1630">• Development offices <li data-bbox="906 1639 1407 1666">• Development change house and laundry. <li data-bbox="906 1675 1209 1702">• Lamp house and crush. <li data-bbox="906 1711 1133 1738">• Medical station. <li data-bbox="906 1747 1334 1774">• Trackless workshop and wash bay. <li data-bbox="906 1783 1171 1809">• Compressor station <li data-bbox="906 1818 1088 1845">• Diesel farm. <li data-bbox="906 1854 1209 1881">• Oil and grease storage, <li data-bbox="906 1890 1283 1917">• Main store and material yard. <li data-bbox="906 1926 1187 1953">• Capital laydown area <li data-bbox="906 1962 1334 1989">• Service water storage and settling. <li data-bbox="906 1998 1193 2024">• Downcast air heating. <li data-bbox="906 2033 1165 2060">• Brake testing ramp <li data-bbox="906 2069 1094 2096">• Main offices

Criteria	JORC Code explanation	Commentary
		<ul style="list-style-type: none"> • Main change houses • Main laundry. • Training centre. • Parking and bus drop off zone • Fire systems • Potable water infrastructure including municipal Interface. • Sewage Infrastructure including municipal Interface. • Gas supply Infrastructure including municipal Interface. • MV electrical infrastructure including municipal Interface. • Explosives accessories magazine. <p><i>Underground Infrastructure</i></p> <p>Underground infrastructure designs take into consideration the life of mine plan and aims to support the underground mining production and development activities. Underground infrastructure comprises:</p> <ul style="list-style-type: none"> • Mine service water systems • Mine dewatering systems, including clear and dirty water pump stations. • Mine electrical reticulation • Control systems and instrumentation • Trackless workshops • Refuelling bays • Underground crushers, tips, and conveyors. <p>The mine service water system is a based on a re-circulation design, with settled water from the mining activities used as service water. This reduces the mine pumping requirement in turn reducing power costs.</p> <p>In terms of electrical reticulation, the Cinovec mining operation will require a bulk power supply of 3.5 MVA. Power will be provided by a local supply authority and it is anticipated it will be at 6kV.</p> <p><i>Underground Ore Handling</i></p> <p>The underground ore handling system is designed for 500 t/h and will comprise the following:</p> <ul style="list-style-type: none"> • A primary tip, equipped with a static grizzly and a hydraulic rock breaker to break oversize lumps; • An ore-pass; • A primary crushing station, equipped with a vibrating grizzly feeder and jaw crusher; • A sacrificial conveyor (CV001), 18 m long, to protect the main decline conveyor;

Criteria	JORC Code explanation	Commentary
		<ul style="list-style-type: none"> A decline conveyor (CV002), 1,146 m long.
<p><i>Metallurgical factors or assumptions</i></p>	<ul style="list-style-type: none"> <i>The metallurgical process proposed and the appropriateness of that process to the style of mineralisation.</i> <i>Whether the metallurgical process is well-tested technology or novel in nature.</i> <i>The nature, amount and representativeness of metallurgical test work undertaken, the nature of the metallurgical domaining applied and the corresponding metallurgical recovery factors applied.</i> <i>Any assumptions or allowances made for deleterious elements.</i> <i>The existence of any bulk sample or pilot scale test work and the degree to which such samples are considered representative of the orebody as a whole.</i> <i>For minerals that are defined by a specification, has the ore reserve estimation been based on the appropriate mineralogy to meet the specifications?</i> 	<p>The beneficiation plant process route consists of crushing, SAG milling, classification, thickening and wet high intensity magnetic separation (WHIMS). The magnetic fraction passes to the Lithium Carbonate Plant (LCP). The non-magnetic fraction is processed by classification, spiral concentration and regrinding of the spiral middlings. The spirals product is a tin / tungsten product. The LCP process route consists of roasting, leaching filtration, impurity removal by ion exchange and crystallization. The testwork program has indicated that the process route selected is appropriate for the style of mineralization of the orebody.</p> <p>The process route selected utilizes standard, industry proven technology. The process route selected was based on the testwork carried out, and on the respective engineering companies' experience on other, similar projects.</p> <p>The samples used for the beneficiation plant testwork were quarter core composites from the drilling campaigns. For the comminution tests, composites were made up of the various ore types to provide an indication of variability. As composites of drill cores were used for the testwork, the samples are considered to be representative of the deposit. The variability in the deposit may be an issue in the plant operation, but additional testwork will be carried out during the feasibility study to inform on this issue. The mass of sample received for the testwork was 150kg, which enabled appropriate sized samples (taking into consideration that the study being carried out is pre-feasibility) to be used for the various tests. The product recoveries were determined from the testwork, factors were not applied.</p> <p>Testwork has produced a saleable lithium carbonate product (>99.5% lithium carbonate) although the levels of fluoride (500 ppm) and silicon (300 ppm) were high. These elements are not generally considered to be deleterious elements in product specifications. Further testwork will be carried out to reduce these levels.</p> <p>No bulk samples were available for the testwork but were not required as the level of study was pre-feasibility. Pilot scale testwork will be carried out during the feasibility study. The composite samples used for the testwork are considered to be representative of the ore-body and suitable for the testwork performed.</p>

Criteria	JORC Code explanation	Commentary
		<p>The specification for the lithium carbonate product is a minimum of 99.5% lithium carbonate. This was achieved in the testwork. Testwork will be carried out during the next phase of the project to further improve on the quality of the product to be produced.</p>
<p><i>Environmental</i></p>	<ul style="list-style-type: none"> • <i>The status of studies of potential environmental impacts of the mining and processing operation. Details of waste rock characterisation and the consideration of potential sites, status of design options considered and, where applicable, the status of approvals for process residue storage and waste dumps should be reported.</i> 	<p>The Company has commenced the Environmental Impact Assessment EIA process with a baseline study, prepared by GET s.r.o an independent Czech based environmental consultancy. This identified the environmental areas to be assessed and determined preliminary outcomes. The underground mine and surface portal is located on the border adjacent to an environmentally sensitive area – Natural park Eastern Krusne hory.</p> <p>The Project area is mostly covered by forests and treeless plateau with bushy growth. The area of Dubí township is covered by farm land (15%) and non-agricultural land (85%), out of that 80% are forests. Intensive biological investigation executed in 2016 identified 20 natural biotops, out of them 4 peat bogs, springheads, waterlogged spruce growths and mountain meadows) are protected within the Natura 2000. Screening process also identified 67 animal species – 2 amphibians, 2 snakes, 51 birds and 11 mammals living in the area. Of them, 14 species are protected. Through the area also runs the regional natural bio corridor K2.</p> <p>The Cinovec Sn/W Lithium Project is governed by Act No.100/2001 Coll., on Environment Impact Assessment (hereinafter referred to as the “EIA Act”). The competent authority is the Ministry of the Environment (Environment Impact Assessment Department). An integrated permit is issued upon completion of the EIA process.</p> <p>In consideration of the exploitation mining licence to be granted and the expected production of the Li-W-Sn ore exceeding 1 Mt a year during the implementation of the Project, the EIA documentation must be prepared and assessed (full-scope EIA Report).</p> <p>The Cinovec Sn/W Lithium Project development documentation shall be structured as follows:</p> <ul style="list-style-type: none"> • details concerning the Notifier, • details concerning the development project, • details concerning the status of the environment in the region concerned, • comprehensive characteristics and assessment of the Project impacts on public health and the environment, • a comparison of project versions (if any),

Criteria	JORC Code explanation	Commentary
		<ul style="list-style-type: none"> • a conclusion, and • a commonly understood summary and annexes (opinion of the Building Authority, opinion of the Nature Protection Authority, expert studies and assessments). <p>The following expert studies and assessments must be compiled during the EIA Documentation preparation stage:</p> <ul style="list-style-type: none"> • noise impact study, • air quality impact study, • biological survey, • human health impact study, • transport impact study, • landscape impact study, and • water quality and hydrology impact study. <p>In this case, with respect to the location of the Project at the border with Germany, the so-called “international assessment” provision applies (Section 13, Act No. 100). This process is more time-demanding – in an international assessment, the Ministry of the Environment may extend the deadlines to present views by up to 30 days; other deadlines (Sec. 12, Act.100) are extended adequately in such a case.</p> <p>EMH commenced the EIA process with the baseline study, prepared by GET, which identified the environmental areas to be assessed and determined preliminary outcomes. The project, mainly the underground mine and surface portal is located in environmentally sensitive area. From that perspective, the EIA will focus particularly on project impacts on European protected areas Natura 2000 (protected birds) and mine water discharge into surface streams due to the content of Beryllium and radioactive components. Considering the long-term mining history in region the Project will not significantly change the situation towards to environment and from that perspective all identified potential problems should be resolvable and EMH do not envision any fatal flaws will be encountered.</p> <p>The Cinovec EIA will focus particularly on Project impacts on European protected areas Natura 2000 (protected birds) and mine water discharge into surface streams. The Company has re-positioned key infrastructure to minimise impacts to both the environment and the community and has placed crushing facilities and fans underground to minimise noise as well as enclosing the mill to further reduce noise and visual impacts. Considering the long-term mining history in region</p>

Criteria	JORC Code explanation	Commentary
		<p>and at the deposit itself, the Project will not significantly impact the environment.</p> <p>Waste Rock</p> <p>Acid-Base accounting (ABA): Acid-Base accounting (ABA) is a screening procedure whereby the acid-neutralising potential (assets) and acid-generating potential (liabilities) of rock samples are determined, and the difference, net neutralising potential (equity), is calculated.</p> <p>Samples were devoid of sulphides and have no potential to generate acid-mine drainage as confirmed through both the ABA and NAG test. However, the Neutralisation Potential of the samples were also very low and samples also had a very low total C content. However, the potential to leach at least As and F which should be further investigated through the column leach testing as these two parameters will also be present in neutral drainage from samples.</p> <p>The addition of acid to samples (ABCC method: 3 g sample in 100 ml water as per AMIRA, 2002) resulted in quick acidification confirming that the samples had almost no Neutralisation Potential. The pH curve is only slightly higher than for the Blank (distilled water).</p> <p>Net Acid Generation (NAG): The single addition NAG test was used to classify the acid generating potential of all 42 samples. The NAG test involves the reaction of a sample with hydrogen peroxide to rapidly oxidise any sulphide minerals contained within a sample. The end result represents a direct measurement of the net amount of acid generated by the sample. This value is commonly referred to as the NAG capacity and is expressed in th is kg H2SO4/tonne.</p> <p>All of the samples tested were classified as non-acid forming. The ICP analysis of the NAG elution did not yield any significant results. This test is more appropriate where the sample have sulphides that can be oxidised with peroxide and ICP analyses indicate metals released.</p> <p>Tailings</p> <p>Tailings produced by the gravity circuit of the FECAB's beneficiation plant and the Residue Filtration Stream produce by the LCP require permanent impoundment in a suitable Tailings Storage Facility (TSF). For the PFS a conservative approach was taken by designing a dry stack tailings facility. Any water from the dry stacked tails is captured and recycled to the LCP process</p>

Criteria	JORC Code explanation	Commentary
		<p>water feed. This approach, although higher in Capex, offers the most environmentally sustainable method of tailings impoundment.</p> <p>Tailings produced by the gravity circuit are filtered in two pressure filters to produce a filter cake with a moisture content of 18%. This moisture content is based of filtration test work performed on a representative tailings sample by Diemme® with the results interpreted by Ausenco and incorporated into the FECAB design.</p> <p>The FECAB filter cakes falls into a bunker below the pressure filters, from where it is collected by a wheel loader and loaded into an articulated truck for transfer to the dry stacks tails tip point. The articulate truck dumps the tailings filter cake where it is spread and compacted by a bulldozer. The estimated cost of the FECAB tailings disposal is \$1.00/ wet tonne.</p> <p>The LCP tailings consist of leach residue filter cake produced by a pressure filter. As with the FECAB, the pressure filter drops the filter cake into a bunker for loading via a wheel loader. The estimated cost for LCP residue disposal is \$1.50/ wet tonne.</p> <p>The loading, trucking and spreading of the tailings will be performed by a local contract earth moving company.</p> <p>Data used as input criteria to the TSF design concept are listed in the table, which is considered adequate for PFS and has been derived from PFS level engineering.</p> <p><i>(Please refer to the announcement on the European Metals Website for the Table described above – www.europeanmet.com.)</i></p> <p>All permits for the tailings dam, waste rock dump and operations will be applied for when appropriate and as governed by Czech law. To date, permits for mine de-watering and preliminary mining permits have been received.</p>
<p>Infrastructure</p>	<ul style="list-style-type: none"> <i>The existence of appropriate infrastructure: availability of land for plant development, power, water, transportation (particularly for bulk commodities), labour, accommodation; or the ease with which the infrastructure can be provided, or accessed.</i> 	<p>Currently, no infrastructure exists at the mine site and therefore allowance has been made for all support facilities required by the planned mining operation. Surface infrastructure has been designed to support the mining plan with consideration of the labour and mechanised equipment requirements of the operation in addition to the movement of rock, men and materials. The infrastructure is divided into two distinct areas, with the area at the portal servicing the initial development requirements and the</p>

Criteria	JORC Code explanation	Commentary												
		<p>second servicing the production phase. The surface infrastructure design includes all facilities and services (such as offices, changehouses, workshops) as well as utilities and reticulation (such as power, water and gas utilities) to support the underground mining activities for the life of mine.</p> <p>Underground infrastructure designs take into consideration the life of mine plan and aims to support the underground mining production and development activities. The underground infrastructure primarily comprises the underground conveyor and crushing system, dewatering facilities, and underground workshops</p>												
Costs	<ul style="list-style-type: none"> <i>The derivation of, or assumptions made, regarding projected capital costs in the study.</i> <i>The methodology used to estimate operating costs.</i> <i>Allowances made for the content of deleterious elements.</i> <i>The source of exchange rates used in the study.</i> <i>Derivation of transportation charges.</i> <i>The basis for forecasting or source of treatment and refining charges, penalties for failure to meet specification, etc.</i> <i>The allowances made for royalties payable, both Government and private.</i> 	<p>The capital and operating cost estimate has been determined through the application of budget quotations, database costs and estimated costs. These costs were applied to material take offs, bill of quantities and estimated quantities derived from the engineering design process. The once the overall capital cost was calculated, the costs are scheduled according to an implementation plan in order to determine the spend over the life of the project.</p> <p><i>(Please refer to the announcement on the European Metals Website for the table showing the Capital Costs – www.europeanmet.com.)</i></p> <p><i>(Please refer to the announcement on the European Metals Website for the table summarising the Operating Costs – www.europeanmet.com.)</i></p>												
Revenue factors	<ul style="list-style-type: none"> <i>The derivation of, or assumptions made regarding revenue factors including head grade, metal or commodity price(s) exchange rates, transportation and treatment charges, penalties, net smelter returns, etc.</i> <i>The derivation of assumptions made of metal or commodity price(s), for the principal metals, minerals and co-products.</i> 	<p>Metal Prices Used</p> <table border="1" data-bbox="917 1518 1460 1809"> <tbody> <tr> <td>Tin (US\$/t metal)</td> <td>22 500</td> </tr> <tr> <td>Tungsten (US\$/MTU)</td> <td>330</td> </tr> <tr> <td>Lithium Carbonate (US\$/t)</td> <td>10 000</td> </tr> <tr> <td>Potassium Sulphate (Potash) (US\$/t)</td> <td>480</td> </tr> </tbody> </table> <p>Exchange Rates Used</p> <table border="1" data-bbox="1029 1910 1343 2038"> <tbody> <tr> <td>USD</td> <td>1.0000</td> </tr> <tr> <td>EUR</td> <td>0.9276</td> </tr> </tbody> </table>	Tin (US\$/t metal)	22 500	Tungsten (US\$/MTU)	330	Lithium Carbonate (US\$/t)	10 000	Potassium Sulphate (Potash) (US\$/t)	480	USD	1.0000	EUR	0.9276
Tin (US\$/t metal)	22 500													
Tungsten (US\$/MTU)	330													
Lithium Carbonate (US\$/t)	10 000													
Potassium Sulphate (Potash) (US\$/t)	480													
USD	1.0000													
EUR	0.9276													

Criteria	JORC Code explanation	Commentary								
Market assessment	<ul style="list-style-type: none"> • <i>The demand, supply and stock situation for the particular commodity, consumption trends and factors likely to affect supply and demand into the future.</i> • <i>A customer and competitor analysis along with the identification of likely market windows for the product.</i> • <i>Price and volume forecasts and the basis for these forecasts.</i> • <i>For industrial minerals the customer specification, testing and acceptance requirements prior to a supply contract.</i> 	<table border="1" data-bbox="1034 241 1347 501"> <tr> <td>CZK</td> <td>25.0500</td> </tr> <tr> <td>CAD</td> <td>1.3082</td> </tr> <tr> <td>AUD</td> <td>1.3212</td> </tr> <tr> <td>GBP</td> <td>0.7965</td> </tr> </table> <p>Lithium is the key driver of the Project. According to Deutsche Bank, global lithium demand increased 15% year on year to 212 kt LCE in 2016, slightly ahead of estimates. Deutsche Bank forecast lithium pricing to remain elevated relative to historical averages, but retrace 15% over 2016 pricing levels. Further, the medium-term outlook is improving and Deutsche Bank has recently lifted their 2019 demand forecast to 380 kt.</p> <p>The ramp up of new EV model sales from major auto companies is generally considered to be the key driver of lithium demand in the short to medium term. Other factors include the increased production from battery manufacturing facilities and the continued inventory build within the supply chain.</p> <p>The Cinovec Project is located centrally and within close proximity to a number of major European car manufacturers.</p> <p>Benchmark expects the average forecasted price range for lithium carbonate 99.95% to be \$ 9,500 to \$ 13,000/tonne (USD) between 2017 and 2020.</p> <p>European Metals has considered this forecast in light of other independent forecasts such as Deutsche Bank, and on generally available lithium market commentary.</p> <p>For the purposes of the PFS with regards to financial modelling, a long-term average price of \$ 10,000/t lithium carbonate FOB has been used. The graph below shows the Deutsche Bank lithium price forecasts to 2025.</p> <p><i>(Please refer to the announcement on the European Metals Website for the graph described above - www.europeanmet.com.)</i></p>	CZK	25.0500	CAD	1.3082	AUD	1.3212	GBP	0.7965
CZK	25.0500									
CAD	1.3082									
AUD	1.3212									
GBP	0.7965									
		<p>A cost comparison shows the project will be in the lowest half of the global cost curve.</p> <p><i>(Please refer to the announcement on the European Metals Website for the cost comparison table described above – www.europeanmet.com.)</i></p>								

Criteria	JORC Code explanation	Commentary
Economic	<ul style="list-style-type: none"> <i>The inputs to the economic analysis to produce the net present value (NPV) in the study, the source and confidence of these economic inputs including estimated inflation, discount rate, etc.</i> <i>NPV ranges and sensitivity to variations in the significant assumptions and input.</i> 	<p>The graph below shows the anticipated supply and demand for lithium.</p> <p><i>(Please refer to the announcement on the European Metals Website for the table showing the anticipated supply and demand for lithium – www.europeanmet.com.)</i></p> <p>There are industry standard specifications for lithium carbonate. The table below shows that the results achieved to-date in testing meets these standards.</p> <p><i>(Please refer to the announcement on the European Metals Website for the table as described above – www.europeanmet.com.)</i></p> <p>The results of the techno-economic evaluation demonstrate that the project is economically viable based on the designs established and the assumptions used in this study. The table below shows that the financial result is positive when considering the time value of money. At a discount rate of 8 per cent, the NPV is 540 million USD and the post-tax IRR is 20.9 per cent.</p> <p><i>(Please refer to the announcement on the European Metals Website for the table as described above – www.europeanmet.com.)</i></p> <p>Sensitivity analysis shows that the project is most sensitive to changes in the price of lithium, as presented in the figure below.</p> <p><i>(Please refer to the announcement on the European Metals Website for the figure described above – www.europeanmet.com.)</i></p>
Social	<ul style="list-style-type: none"> <i>The status of agreements with key stakeholders and matters leading to social licence to operate.</i> 	<p>The Cinovec project has been included in the Czech Government programme for the restructuring of the region Usti in the context of Government support of the regions damaged by the former coal mining. The projects included in this Government programme will have the full support of the Central Government, regional Governments and all the social partners within the region. The Ministry of industry, in collaboration with the Ministry of Foreign Affairs also prepare a Memorandum of cooperation between the Czech Republic and Australia in which the Government of the Czech Republic declares full support for the Cinovec project.</p>
Other	<ul style="list-style-type: none"> <i>To the extent relevant, the impact of the following on the project and/or on the estimation and classification of the Ore</i> 	<p>There is a clear process for the award of Mining Permits in the Czech Republic. These include</p>

Criteria**JORC Code explanation**

- Reserves:*
- Any identified material naturally occurring risks.
 - The status of material legal agreements and marketing arrangements.
 - The status of governmental agreements and approvals critical to the viability of the project, such as mineral tenement status, and government and statutory approvals. There must be reasonable grounds to expect that all necessary Government approvals will be received within the timeframes anticipated in the Pre-Feasibility or Feasibility study. Highlight and discuss the materiality of any unresolved matter that is dependent on a third party on which extraction of the reserve is contingent.

Commentary

placing the reserves on “State Balance” which has largely been completed. Subsequently a Preliminary Mining permit is issued. This has been received for a portion of the deposit and work is on-going to gain a permit for the remaining area. Subsequent to this, a Mining Permit can be issued once all other requirements are met, ie an approved EIA, land zoning change for certain works etc.

The lands needed for the construction of the mine, the transport pipeline and the processing plant are mostly owned by the state and a private owner Forests North, who are all supportive of the project.

Marketing agreements need to be entered into by the Company. The Company has commenced discussions with offtakers and with the forecast supply/demand curve is confident that any battery grade lithium will be readily sold into the market.

Classification

- The basis for the classification of the Ore Reserves into varying confidence categories.
- Whether the result appropriately reflects the Competent Person’s view of the deposit.
- The proportion of Probable Ore Reserves that have been derived from Measured Mineral Resources (if any).

The classification of the Ore Reserves is shown below:

CINOVEC ORE RESERVES SUMMARY					
Category	Tonnes	Li	Li₂O	Sn	W
	(Millions)	%	%	%	%
Proven Ore Reserves	0	0	0	0	0
Probable Ore Reserves	34.5	0.30	0.65	0.09	0.03
Total Ore Reserves	34.5	0.30	0.65	0.09	0.03

This reflects the Competent Persons view of the deposit.

All Ore Reserves declared are Probable Ore Reserves and are derived from Indicated Mineral Resources. The classification is based on two factor being:

- Engineering study work has only progressed to preliminary feasibility levels of accuracy thus confidence levels in the engineering and costing are only appropriate for Probable Ore Reserves.
- The Mineral Resources converted to Ore Reserves are all at the Indicated level of confidence which will only support conversion to Probable Ore Reserve.

Criteria	JORC Code explanation	Commentary
Audits or reviews	<ul style="list-style-type: none"> The results of any audits or reviews of Ore Reserve estimates. 	No external audits of the ore reserve have been undertaken to date
Discussion of relative accuracy/confidence	<ul style="list-style-type: none"> Where appropriate a statement of the relative accuracy and confidence level in the Ore Reserve estimate using an approach or procedure deemed appropriate by the Competent Person. For example, the application of statistical or geostatistical procedures to quantify the relative accuracy of the reserve within stated confidence limits, or, if such an approach is not deemed appropriate, a qualitative discussion of the factors which could affect the relative accuracy and confidence of the estimate. The statement should specify whether it relates to global or local estimates, and, if local, state the relevant tonnages, which should be relevant to technical and economic evaluation. Documentation should include assumptions made and the procedures used. Accuracy and confidence discussions should extend to specific discussions of any applied Modifying Factors that may have a material impact on Ore Reserve viability, or for which there are remaining areas of uncertainty at the current study stage. It is recognised that this may not be possible or appropriate in all circumstances. These statements of relative accuracy and confidence of the estimate should be compared with production data, where available. 	<p>The accuracy and confidence level of the selected modifying factors are considered to be commensurate with a preliminary feasibility study.</p> <p>The accuracy and confidence in the cost estimation, which is based primarily on the work completed by the various consulting groups are considered to be at pre-feasibility study levels of accuracy, typically to $\pm 25\%$ accuracy.</p>